



# AFP3105FR

## URETHANE CASTING MATERIAL SPECIFICATIONS

### Highlights

- Passes 60 second burn test at 0.043 inch
- Meets FAR 25.853a requirements per Appendix F, Part 1 (a1)(ii)

### Applications

- Durable, high-impact strength urethane with FAR 25.853 flammability rating

### TYPICAL PHYSICAL PROPERTIES

MECHANICAL PROPERTIES	TEST METHOD	ENGLISH	METRIC
Color/Appearance	Visual	Translucent Amber	Translucent Amber
Elongation at Break	ASTM D638	25%	25%
Compressive Modulus	ASTM D695	406,265 psi	2,801 MPa
Compressive Strength	ASTM D695	12,878 psi	90 MPa
Density	ASTM D792	0.0435 lb/in <sup>3</sup>	1.20 g/cc
Flexural Modulus	ASTM D790	435,747 psi	3,004 MPa
Flexural Strength	ASTM D790	16,743 psi	115 MPa
Glass Transition Temperature E (onset)	TMA	179°F	82°C
Glass Transition Temperature Tg (peak)	TMA	203°F	95°C
Izod Impact Strength (method A, notched)	ASTM D256	1.42 ft-lb/in	75 J/m
Tensile Modulus	ASTM D638	390,220 psi	2,690 MPa
Tensile Strength	ASTM D638	10,676 psi	73 MPa
Flammability per FAA FAR Volume III, Part 25.853	FAA	Passes 60 sec burn test at 0.043 inch	Passes 60 sec burn test at 0.043 inch

The information presented represents typical values intended for reference and comparison purposes only. It should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, color etc. Actual values will vary with build conditions. Product specifications are subject to change without notice.

The performance characteristics of these materials may vary according to application, operating conditions, or end use. Each user is responsible for determining that the material is safe, lawful, and technically suitable for the intended application. Stratasys makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement.