



Nylon 12 AF

LASER SINTERING MATERIAL SPECIFICATIONS

Highlights

- Aluminum filled composite polyamide producing strong, stiff parts with a grey metallic appearance
- Improved tensile modulus and flex modulus
- Good wear resistance and detail reproduction
- Suitable for parts requiring superior surface finish

Applications

- Aerospace, automotive, packaging, electronics, consumer products, industrial, and OEM products
- Functional components
- Illustrative models with metallic appearance
- Jigs and fixtures

TYPICAL PHYSICAL PROPERTIES

MECHANICAL PROPERTIES	TEST METHOD	ENGLISH	METRIC
Color/Appearance	Visual	Grey Metallic	Grey Metallic
Density	DIN 53466	0.049 lb/in ³	1.36 g/cm ³
Elongation at Break	ASTM D638	1.5 - 3.5%	1.5 - 3.5%
Flexural Strength	ASTM D790	7,832 psi	54 MPa
Flexural Modulus	ASTM D790	289 ksi	1,990 MPa
Heat Deflection Temp @66 psi	ASTM D648	351°F	177°C
Heat Deflection Temp @264 psi	ASTM D648	279°F	137°C
Tensile Modulus	ASTM D638	374 ksi	2,580 MPa
Tensile Strength	ASTM D638	4,628 psi	32 MPa
As Processed Surface Finish	Up-facing surfaces	300 - 400 RA	7.6 - 10.2 μm
Volume Resistivity (74°F, 35.4% RH)	—	—	2.5E+03 ohms-cm
Surface Resistant (74°F, 35.4% RH)	—	—	3.1E+10 ohms-cm

The information presented represents typical values intended for reference and comparison purposes only. It should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, color etc. Actual values will vary with build conditions. Product specifications are subject to change without notice.

The performance characteristics of these materials may vary according to application, operating conditions, or end use. Each user is responsible for determining that the material is safe, lawful, and technically suitable for the intended application. Stratasys makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement.